

Client: DIXON SAND (PENRITH) PTY LTD
PO BOX 148
PENRITH NSW 2751

Job No 7555/1
Date: 05/04/2019
Tested By: DLS
Checked By: AK

Project: MATERIAL ANALYSIS
MATERIAL TESTING - 4610 OLD NORTHERN ROAD, MARROOTA

TEST RESULTS

| TEST PROCEDURE AS1141.11.1 (DRY SIEVING), 12 | | |
|--|---------------------------|---|
| Material Description | Bricklaying SAND (Yellow) | |
| Sieve Analysis | | |
| Laboratory Number | 7555/1-337 | |
| <u>Sieve Size</u> | Percentage Passing | Pre-treatment Nil - Standard Oven Drying |
| 9.5mm | 100 | <div style="border: 1px solid black; padding: 5px;"> <p>AS1141.12 Materials finer than 75 microns in Aggregates (by washing) % Passing</p> <p style="text-align: center; font-size: 1.2em;">11.1</p> </div> |
| 4.75mm | 100 | |
| 2.36mm | 95 | |
| 1.18mm | 83 | |
| 600 microns | 41 | |
| 300 microns | 8 | |
| 150 microns | 1 | |
| 75 microns | 0.3 | |
| Date Sampled | 14/02/2019 | |
| Sampling Procedure | Sampled by Client | |
| Sampling Location | Ex Maroota Quarry | |

Form No: R 025 Version 05 06/13 - issued by ER



Accredited for compliance with ISO/IEC 17025.

A Kench

05/04/2019

Approved Signatory



Nata Accreditation Number 2734
Corporate Site Number 2727

Head Office:
34 Borec Road, Penrith NSW 2750
P O Box 880 Penrith NSW 2751
Telephone: (02) 4722 2744 Facsimile: (02) 4722 2777

Prestons Laboratory:
Unit 4, 18-20 Whyalla Place, Prestons NSW 2170
Telephone: (02) 9607 6111 Facsimile: (02) 9607 6200