

Client: DIXON SAND (PENRITH) PTY LTD
PO BOX 148
PENRITH NSW 2751

Job No: 7555/1
Date: 27/06/2019
Tested By: BN
Checked By: AK

Project: MATERIAL ANALYSIS
MATERIAL TESTING - 4610 OLD NORTHERN ROAD, MAROOTA

TEST RESULTS

Page 1 of 1

TEST PROCEDURE AS1141.11.1 (DRY SIEVING), 12			
Material Description	Bricklaying SAND (White)		
Sieve Analysis			
Laboratory Number	7555/1-344		
<u>Sieve Size</u>	Percentage Passing	Pre-treatment Nil - Standard Oven Drying	
9.5mm	100	<div style="border: 1px solid black; padding: 5px;"> <p>AS1141.12 Materials finer than 75 microns in Aggregates (by washing) % Passing</p> <hr/> <p style="text-align: center; font-size: 1.2em;">10.1</p> </div>	
4.75mm	100		
2.36mm	95		
1.18mm	86		
600 microns	63		
300 microns	16		
150 microns	4		
75 microns	1.2		
Date Sampled	12/06/2019		
Sampling Procedure	Sampled by Client. Results apply to sample as received		
Sampling Location	Ex Maroota Quarry		

Form No: R 025 Version 05/06/13 - issued by ER



Nata Accreditation Number 2734
Corporate Site Number 2727

Accredited for compliance with ISO/IEC 17025.

A Kench

27/06/2019

Approved Signatory



Head Office:
34 Borec Road, Penrith NSW 2750
P O Box 880 Penrith NSW 2751
Telephone: (02) 4722 2744 Facsimile: (02) 4722 2777

Prestons Laboratory:
Unit 4, 18-20 Whyalla Place, Prestons NSW 2170
Telephone: (02) 9607 6111 Facsimile: (02) 9607 6200

email: info@geotech.com.au www.geotech.com.au

