

Client: DIXON SAND (PENRITH) PTY LTD  
PO BOX 148  
PENRITH NSW 2751

Job No 7555/1  
Date: 21/07/2020  
Tested By: SS  
Checked By: AK

Project: MATERIAL ANALYSIS  
MATERIAL TESTING - 4610 OLD NORTHERN ROAD, MARROOTA

## TEST RESULTS

Page 1 of 1

TEST PROCEDURE AS1141.11.1 (DRY SIEVING)	
Material Description	Bricklaying SAND (Yellow)
Sieve Analysis	
Laboratory Number	7555/1-392
<u>Sieve Size</u>	Percentage Passing
9.5mm	100
4.75mm	100
2.36mm	98
1.18mm	93
600 microns	68
300 microns	23
150 microns	6
75 microns	10.6
Date Sampled	02/07/2020
Sampling Procedure	Sampled by Client - Tested as received
Sampling Location	Ex Maroota Quarry

Pre-treatment  
Nil - Standard Oven Drying

**AS1141.12 Materials finer than 75 microns in Aggregates (by washing) % Passing**

10.6

Form No: R 025 Version 05 06/13 - issued by ER



Nata Accreditation Number 2734  
Corporate Site Number 2727

Head Office:  
34 Borec Road, Penrith NSW 2750  
P O Box 880 Penrith NSW 2751  
Telephone: (02) 4722 2744 Facsimile: (02) 4722 2777

Accredited for compliance with ISO/IEC 17025.

A Kench

21/07/2020

Approved Signatory



Prestons Laboratory:  
Unit 4, 18-20 Whyalla Place, Prestons NSW 2170  
Telephone: (02) 9607 6111 Facsimile: (02) 9607 6200

email: info@geotech.com.au www.geotech.com.au