

Client: DIXON SAND (PENRITH) PTY LTD
 PO BOX 148
 PENRITH NSW 2751

Job No 7555/1
 Date Tested: 30/11/2020
 Tested By: HW
 Checked By: AK

Project: MATERIAL ANALYSIS
 MATERIAL TESTING - 4610 OLD NORTHERN ROAD, MAROOTA

TEST RESULTS

Page 1 of 1

TEST PROCEDURE AS1141.11.1 (DRY SIEVING)	
Material Description	Bricklaying SAND (Yellow)
Sieve Analysis	
Laboratory Number	7555/1-411
<u>Sieve Size</u>	Percentage Passing
	Pre-treatment Nil - Standard Oven Drying
9.5mm	100
4.75mm	100
2.36mm	100
1.18mm	83
600 microns	50
300 microns	13
150 microns	3
75 microns	0.6
Date Sampled	17/11/2020
Sampling Procedure	Sampled by Client - Tested as received
Sampling Location	Ex Maroota Quarry

AS1141.12 Materials finer than 75 microns in Aggregates (by washing) % Passing

10.5

Form No: R 025 Version 05 06/13 - issued by ER



Nata Accreditation Number 2734
 Corporate Site Number 2727

Head Office:
 34 Borec Road, Penrith NSW 2750
 P O Box 880 Penrith NSW 2751
 Telephone: (02) 4722 2744 Facsimile: (02) 4722 2777

Accredited for compliance with ISO/IEC 17025.

A Kench

30/11/2020

Approved Signatory



Prestons Laboratory:
 Unit 4, 18-20 Whyalla Place, Prestons NSW 2170
 Telephone: (02) 9607 6111 Facsimile: (02) 9607 6200

email: info@geotech.com.au www.geotech.com.au