

Client: DIXON SAND (PENRITH) PTY LTD  
 PO BOX 148  
 PENRITH NSW 2751

Job No 7555/1  
 Date Tested: 15/01/2021  
 Tested By: HW  
 Checked By: AK

Project: MATERIAL ANALYSIS  
 MATERIAL TESTING - 4610 OLD NORTHERN ROAD, MAROOTA

## TEST RESULTS

Page 1 of 1

TEST PROCEDURE AS1141.11.1 (DRY SIEVING)	
Material Description	Coarse SAND
Sieve Analysis	
Laboratory Number	7555/1-412
<u>Sieve Size</u>	Percentage Passing
	Pre-treatment Nil - Standard Oven Drying
9.5mm	100
4.75mm	100
2.36mm	90
1.18mm	76
600 microns	53
300 microns	18
150 microns	3
75 microns	1.3
Date Sampled	19/12/2020
Sampling Procedure	Sampled by Client - Tested as received
Sampling Location	Ex Maroota Quarry

Form No: R 025 Version 05 06/13 - issued by ER



Nata Accreditation Number 2734  
 Corporate Site Number 2727

Head Office:  
 34 Borec Road, Penrith NSW 2750  
 P O Box 880 Penrith NSW 2751  
 Telephone: (02) 4722 2744 Facsimile: (02) 4722 2777

Accredited for compliance with ISO/IEC 17025.

A Kench

18/01/2021

Approved Signatory



Prestons Laboratory:  
 Unit 4, 18-20 Whyalla Place, Prestons NSW 2170  
 Telephone: (02) 9607 6111 Facsimile: (02) 9607 6200

email: info@geotech.com.au www.geotech.com.au