

Client: DIXON SAND (PENRITH) PTY LTD  
PO BOX 148  
PENRITH NSW 2751

Job No 7555/1  
Date Tested: 15/01/2021  
Tested By: BC  
Checked By: AK

Project: MATERIAL ANALYSIS  
MATERIAL TESTING - 4610 OLD NORTHERN ROAD, MAROOTA

## TEST RESULTS

Page 1 of 1

TEST PROCEDURE AS1141.11.1 (DRY SIEVING)		
Material Description	Fine SAND	
Sieve Analysis		
Laboratory Number	7555/1-413	
<u>Sieve Size</u>	Percentage Passing	Pre-treatment Nil - Standard Oven Drying
9.5mm	100	
4.75mm	100	
2.36mm	100	
1.18mm	97	
600 microns	73	
300 microns	21	
150 microns	4	
75 microns	1.5	
Date Sampled	08/12/2020	
Sampling Procedure	Sampled by Client - Tested as received	
Sampling Location	Ex Maroota Quarry	

Form No: R 025 Version 05 06/13 - issued by ER



Nata Accreditation Number 2734  
Corporate Site Number 2727

Head Office:  
34 Borec Road, Penrith NSW 2750  
P O Box 880 Penrith NSW 2751  
Telephone: (02) 4722 2744 Facsimile: (02) 4722 2777

Accredited for compliance with ISO/IEC 17025.

A Kench

18/01/2021

Approved Signatory



Prestons Laboratory:  
Unit 4, 18-20 Whyalla Place, Prestons NSW 2170  
Telephone: (02) 9607 6111 Facsimile: (02) 9607 6200