

Client: DIXON SAND (PENRITH) PTY LTD
 PO BOX 148
 PENRITH NSW 2751

Job No 7555/1
 Date Tested: 15/01/2021
 Tested By: BC
 Checked By: AK

Project: MATERIAL ANALYSIS
 MATERIAL TESTING - 4610 OLD NORTHERN ROAD, MAROOTA

TEST RESULTS

Page 1 of 1

| TEST PROCEDURE AS1141.11.1 (DRY SIEVING) | |
|--|---|
| Material Description | Bricklaying SAND (White) |
| Sieve Analysis | |
| Laboratory Number | 7555/1-418 |
| <u>Sieve Size</u> | Percentage Passing |
| | Pre-treatment Nil - Standard Oven Drying |
| 9.5mm | 100 |
| 4.75mm | 100 |
| 2.36mm | 98 |
| 1.18mm | 92 |
| 600 microns | 48 |
| 300 microns | 14 |
| 150 microns | 3 |
| 75 microns | 0.9 |
| Date Sampled | 11/01/2021 |
| Sampling Procedure | Sampled by Client - Tested as received |
| Sampling Location | Ex Maroota Quarry |

AS1141.12 Materials finer than 75 microns in Aggregates (by washing) % Passing

11.7

Form No: R 025 Version 05 06/13 - issued by ER



Nata Accreditation Number 2734
 Corporate Site Number 2727

Head Office:
 34 Borec Road, Penrith NSW 2750
 P O Box 880 Penrith NSW 2751
 Telephone: (02) 4722 2744 Facsimile: (02) 4722 2777

Accredited for compliance with ISO/IEC 17025.

A Kench

18/01/2021

Approved Signatory



Prestons Laboratory:
 Unit 4, 18-20 Whyalla Place, Prestons NSW 2170
 Telephone: (02) 9607 6111 Facsimile: (02) 9607 6200

email: info@geotech.com.au www.geotech.com.au