

Client: DIXON SAND (PENRITH) PTY LTD  
 PO BOX 148  
 PENRITH NSW 2751

Job No: 7555/1  
 Date: 15/08/2017  
 Tested By: DS  
 Checked By: AK

Project: MATERIAL ANALYSIS  
 MATERIAL TESTING - 4610 OLD NORTHERN ROAD, MARROOTA

## TEST RESULTS

TEST PROCEDURE AS1141.11.1 (DRY SIEVING), 12		
Material Description	Bricklaying SAND (White)	
Sieve Analysis		
Laboratory Number	7555/1-294	
<u>Sieve Size</u>	Percentage Passing	Pre-treatment Nil - Standard Oven Drying
9.5mm	100	<b>AS1141.12 Materials finer than 75 microns in Aggregates (by washing) % Passing</b>  <div style="border: 1px solid black; padding: 10px; text-align: center;"> <b>11.3</b> </div>
4.75mm	100	
2.36mm	92	
1.18mm	75	
600 microns	25	
300 microns	4	
150 microns	1	
75 microns	0.1	
Date Sampled	15/06/2017	
Sampling Procedure	Sampled by Client	
Sampling Location	Ex Maroota Quarry	

Form No: R 025 Version 05 06/13 - issued by ER



Nata Accreditation Number 2734  
 Corporate Site Number 2727

Accredited for compliance with ISO/IEC 17025.

A Kench

15/08/2017

Approved Signatory



Head Office:  
 34 Borec Road, Penrith NSW 2750  
 P O Box 880 Penrith NSW 2751  
 Telephone: (02) 4722 2744 Facsimile: (02) 4722 2777

Prestons Laboratory:  
 Unit 4, 18-20 Whyalla Place, Prestons NSW 2170  
 Telephone: (02) 9607 6111 Facsimile: (02) 9607 6200