

Client: DIXON SAND (PENRITH) PTY LTD  
PO BOX 148  
PENRITH NSW 2751

Job No 7555/1  
Date: 26/8/2016  
Tested By: DS  
Checked By: EVN

Project: MATERIAL ANALYSIS  
MATERIAL TESTING - 4610 OLD NORTHERN ROAD, MARROOTA

### TEST RESULTS

TEST PROCEDURE AS1141.11.1 (DRY SIEVING), 12		
Material Description	Bricklaying SAND (Yellow)	
Sieve Analysis		
Laboratory Number	7555/1-273	
<u>Sieve Size</u>	Percentage Passing	Pre-treatment Nil - Standard Oven Drying
9.5mm	100	<div style="border: 1px solid black; padding: 5px;"> <p><b>AS1141.12 Materials finer than 75 microns in Aggregates (by washing) % Passing</b></p> <p style="text-align: center; font-size: 1.2em;"><b>8.9</b></p> </div>
4.75mm	99	
2.36mm	94	
1.18mm	84	
600 microns	43	
300 microns	10	
150 microns	2.7	
75 microns	0.3	
Date Sampled	16/6/2016	
Sampling Procedure	Sampled by Client	
Sampling Location	Ex Maroota Quarry	

Form No: R 025 Version 05 06/13 - issued by ER




Accredited for compliance with ISO/IEC 17025.

E Van Niekerk

26/8/2016

Approved Signatory

Nata Accreditation Number 2734  
Corporate Site Number 2727



Head Office:  
34 Borec Road, Penrith NSW 2750  
P O Box 880 Penrith NSW 2751  
Telephone: (02) 4722 2744 Facsimile: (02) 4722 2777

Prestons Laboratory:  
Unit 4, 18-20 Whyalla Place, Prestons NSW 2170  
Telephone: (02) 9607 6111 Facsimile: (02) 9607 6200