

Client: DIXON SAND (PENRITH) PTY LTD  
 PO BOX 148  
 PENRITH NSW 2751

Job No: 7555/1  
 Date: 17/05/2016  
 Tested By: DS  
 Checked By: AK

Project: MATERIAL ANALYSIS  
 MATERIAL TESTING - 4610 OLD NORTHERN ROAD, MARROOTA

### TEST RESULTS

TEST PROCEDURE AS1141.11.1 (DRY SIEVING), 12		
Material Description	Bricklaying SAND (Yellow)	
Sieve Analysis		
Laboratory Number	7555/1-267	
<u>Sieve Size</u>	Percentage Passing	Pre-treatment Nil - Standard Oven Drying
9.5mm	100	<div style="border: 1px solid black; padding: 5px; text-align: center;"> <b>AS1141.12 Materials finer than 75 microns in Aggregates (by washing) % Passing</b>   <div style="border: 1px solid black; padding: 10px; display: inline-block; margin: 10px auto; width: 80px; text-align: center;"> <b>10.8</b> </div> </div>
4.75mm	99	
2.36mm	96	
1.18mm	93	
600 microns	70	
300 microns	19	
150 microns	3	
75 microns	0.5	
Date Sampled	09/05/2016	
Sampling Procedure	Sampled by Client	
Sampling Location	Ex Maroota Quarry	

Form No: R 025 Version 05 06/13 - issued by ER



Nata Accreditation Number 2734  
 Corporate Site Number 2727

Head Office:  
 34 Borec Road, Penrith NSW 2750  
 P O Box 880 Penrith NSW 2751  
 Telephone: (02) 4722 2744 Facsimile: (02) 4722 2777

Accredited for compliance with ISO/IEC 17025.

A Kench 18/05/2016

Approved Signatory



Prestons Laboratory:  
 Unit 4, 18-20 Whyalla Place, Prestons NSW 2170  
 Telephone: (02) 9607 6111 Facsimile: (02) 9607 6200